



Test Report

Date : 2019-08-28
No. : ST19080231

Page 1 of 2

Applicant(Code:09300047) : FU CHI TEXTILE DECORATION (SHANGHAI)CO.,LTD
Room 6,building 303,No.1158 Center Road, Songjiang District,
Shanghai

Attn: Xie Lianxiang

Description of Samples : One (1) piece of submitted sample(s) said to be
Fabric
Composition: Polyester
Style No.: SV280

**Conditions of Received
Samples** :



Date Samples Received : 2019-08-23

Date Tested : 2019-08-23 to 2019-08-28

Investigation Requested : Selected test(s) as detailed herein.

Remarks : -


Eddy, Yi
Authorized Signatory





Test Report

Date : 2019-08-28
No. : ST19080231

Page 2 of 2

Test Results:

1. Flammability Test

Test Method: CA TB 117:2013 Section 1: Cover fabric test

Conditioning:

Condition test specimens and cigarettes prior to the test for a minimum of 24 hours at $21 \pm 3^{\circ}\text{C}$ ($70^{\circ} \pm 5^{\circ}\text{F}$) and less than 53% relative humidity. If conditions in the test area are not the same as in the conditioning area, tests should begin within 10 minutes of removal of samples from conditioning area.

Test Result:

<u>Specimen</u>	<u>Obvious Ignition</u>	<u>Smolder Time</u>	<u>Vertical char length (nearest 2.5 mm)</u>	<u>Comment</u>
1	N.O.	20 min 18 sec	20.0	Pass
2	N.O.	20 min 20 sec	20.0	
3	N.O.	20 min 25 sec	20.0	

Requirement:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a) The mock-up test specimen continues to smolder after the 45 minute test duration;
 - b) A vertical char length of more than 1.8 inches (45 mm) develops on the cover fabric.
 - c) The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

***** End of Test Report *****